

EPOXY FILLER WITH FIBREGLASS



Technical information

Product for professional use only

Product components :

Fibreglass Epoxy Filler – component A
Hardening Agent for Fibreglass Epoxy Filler – component B

Volume:

component A + component B : 750 g, 7,5 kg.

Product Description :



Due to the content of fibreglass, the product is characterized by enhanced durability, greater binding power and a lower exothermic reaction when applied onto a large surface. It shows adhesion to a wide variety of surfaces, including surfaces made from metal, laminates, etc. It forms a firm and flexible surface, resistant to chemical conditions and chemicals. Does not absorb water or humidity after setting. Contraction after setting < 0,5 %. Characterized by excellent adhesiveness to all types of surfaces.

Uses :

Recommended for the repair of swimming equipment, above and below the water line. Characterized by excellent adhesiveness to all types of surfaces, including: polyester and epoxy laminates, wood, steel, fibre, and other materials. A filler of a wide range of uses, mainly for filling deficits in polyester laminates, applying onto surfaces which should be reinforced mechanically.

Physiochemical characteristics :

Filler colour, comp. A: white

Filler finish: half matte

Weight of 1 litre = 1800 g

Hardening agent colour, comp B: light green

Finish of comp. B: half matte

Weight of 1 litre = 900 g


Mixture colour: light green

Preparing the surface:



Degrease the work surface, sand with a sandpaper of P40-P280 granulation. Remove dust and degrease again. Wash off salts and any other contaminations with fresh water.

Component mixing proportions :



units of weight: (g)

units of volume: (l)4

Filler : Hardening Agent

100 : 50

1 : 1

Do not exceed the recommended amount of hardener!

Mix the ingredients together until a uniform colour is obtained. Do not mix bigger amount of the product than the one that can be used within the use-by date. One should pay particular attention to the bottom and the walls of a container in which the components were mixed. Manual mixing brings the risk of imprecision and lowering the quality of material. Adding too little or too big amount of the hardener compared to the recommended proportion, will not cause a quicker or slower reaction of hardening. It will only cause incomplete hardening of the resin which will not be able to be repaired.

Application time :

after mixing them together with the hardener is 25 minutes.

Application conditions:

The minimum temperature for application of epoxy fillers is +10°C. Best results can be achieved at the temperature of 20-25°C. The relative humidity should not exceed 70%.

Application :



Apply with a putty knife. Do not exceed the thickness of 3 mm in one layer. Every successive layer should be approximately by 10% thinner than the previous one.

EPOXY FILLER WITH FIBREGLASS



Technical information

Product for professional use only

Setting time :



24 hours at 20°C.

Temperature below 20°C significantly extend the setting time.

At the temperature of $< 10^{\circ}\text{C}$ the filler does not polymerize.

The given times must be considered as guidelines only. The actual setting time may be shorter or longer and depends on film thickness, ventilation, humidity, etc.

Theoretical Output :

about 3,7 m²/kg for the thickness of 200 µm

Further Work :

After setting, the surface should be sanded:

- general sanding: P80-P120,
- finishing work: P120-P240.

Epoxy Filler with fibreglass can be finished with:

- any Sea-Line epoxy system,
- any Sea-Line polyurethane system

Caution: Before applying a polyurethane system like gelcoat or topcoat, it is recommended to cover the filler with a thin layer of Sea-Line GRP Epoxy Lightprimer.

General Cautions :



- During the work, it is necessary to use a functional personal protective equipment. One should protect eyes and respiratory tracts.
- Rooms should be well ventilated.
- Tools should be washed directly after application
- Minimum application temperature is $+10^{\circ}\text{C}$

Caution: In the interest of safety, always act in accordance with the data included in the technical data sheet for a given product.

Storage :



Product components should be kept in tightly sealed containers, in dry and cool spaces, away from the sources of flames, heat, and sun rays.



Caution: After every use, containers should be closed immediately!
Protect hardener from overheating!

Expiration date :



Filler - 24 months from the date of production.

Hardening agent - 24 months from the date of production.

Quality Guarantee :

Production, quality control, and the realization of deliveries fulfill the demands of ISO 9001 and 14001 standards.

All information is based on scrupulous laboratory research and many years of experience. Our position of market leadership does not free us from constant quality control of our products. However, we do not accept responsibility for the effects of improper use or storage of our products, or for the effects of using our products in any way contrary to the standards of good workmanship.

TROTON sp. z o.o. Zabrowo.