COMPATIBILITY CHART ANTIFOULING Sea-Line®			NEW PAINT SEA-LINE®				
			SELF-POLISHING ANTIFOULING	SELF-POLISHING ANTIFOULING ALU PLUS	HARD ANTIFOULING	SEAGUARD fouling stop	
CURRENT COAT ANTIFOULING (only in good condition)	SEA-LINE®	 SELF-POLISHING SELF-POLISHING ALU PLUS HARD SEAGUARD 	*	<u>*</u>	<u>*</u>	<u>*</u>	
	INTERNATIONAL	 MICRON EXTRA MICRON EXTRA 2 CRUISER UNO CRUISER BRIGHT WHITE INTERSPEED ULTRA 2 VC OFSHORE EU 	*	*	*	<u>*</u>	
	INTE	■ MICRON OPTIMA ■ VC 17m EXTRA ■ TRILUX 33					
	HEMPEL	 Ocean Performer Mille Dynamic Hard Racing Cruisung Performer/ Tiger Cruising Glide Cruise Tiger Extra / Titan ultra 	*	*	*	<u>*</u>	
		Hard Racing Ultra			*		
	SEA JET	 031 (Samurai) 033 (Shogun) 034 (Emperor) 037 (Costal) 039 (Platinum) 	*	<u>*</u>	*	<u>*</u>	
	ОТНЕВ	 OLIVA VSE PLASTIMO Classic PLASTIMO Performance PLASTIMO Racing SOROMAP AF1 SOROMAP AF2 SOROMAP AFC+ 	<u>*</u>	<u>*</u>	*	4	
Do not risk! If existing antifouling coat is in Bad condition, remove it!							
Basic recommendation for surface preparation and paint application Sea-Line®:							
 Clean old surface with water under pressure (remove splinters and repair damage on the surface) Abrade P100-P240 all surface places after repair or grinded surfaces from antifouling paint protect using 1K UNIVERSAL PRIMER Sea-Line Apply 1-3 layers of Sea-Line antifouling 							
	<u>*</u>	 Remove all layers of old antyfouling Abrade P100-P240 all surface Apply minimum 1 layer primer: 2K Epoxy Lightprimer 5:1 Sea-Line - laminates (GRP) 2K Epoxy Anticorrosive 4:1 Sea-Line - steel, aluminium 2K Epoxy Woodprimer 10:4 Sea-Line - wood 1K UNIVERSAL PRIMER Sea-Line - laminates (GRP), steel, wood Apply by 1-3 of layers Sea-Line antifouling 					
		When using the product in a sr	> Use biocides safely. Always read the label and product information before use				

Please follow safety instructions from the technical data sheet for hazardous chemical and follow Polish

Avoid contact of liquid with eyes and skin

workplace safety laws